



## Key Facts

- Extends the operation life of many wearing parts
- Excellent abrasion resistance to moderate impact
- Deposits weld metal of high toughness

## Description

Bronze-coated solid wire mostly used with semiautomatic and automatic procedures, for hardfacing wheels, rolling mill rollers tracks, sliding rollers, screws, mill crushing jaws and mill wheels, where excellent resistance to abrasion is required especially when accompanied by shocks, and blows, and for hardfacing wearing components such as excavation buckets and teeth and surfaces subject to abrasion and heavy loads. A cushion layer deposited with basic-coated electrode or basic flux cored wire is essential only with hard-to-weld steels. To be used under the shield of Ar+CO<sub>2</sub>.

Precision layer wound, copper coated, hard facing MIG wire, depositing weld metal with a hardness of 54-58HRC. The weld can handle abrasion, moderate impact and metal-to-metal wear.

## Classifications, Approvals & Conformances

AS/NZS 2576 1855-B6  
 DIN 8555 MSG6-4Z-60  
 WN 1.4718  
 EN 14700: S Fe8

## Recommended Shielding Gas

Ar+CO<sub>2</sub>

## Welding Positions

All positions



All Positions

## Applications

Ideal for use on components that are subject to high abrasion like bucket lips, screw conveyors, drilling tools, shear blades and sand dredgers.

- Suitable for facing guillotine blades, punch dies
- Hardfacing earth engaging equipment including- buckets, augers, tynes

## Typical Wire Analysis

C - Carbon	Mn - Manganese	Si - Silicon	Cr - Chromium
0.43 – 0.47	0.30 – 0.60	2.80 – 3.20	8.90 – 9.50
Ni - Nickel	Mo - Molybdenum	S - Sulphur	P - Phosphorus
< 0.20	< 0.30	< 0.02	0.02
Cu - Copper	Al - Aluminium		
< 0.20	< 0.10		

## Typical Weld Mechanical Properties

<b>Hardness:</b>	> 58HRc
------------------	---------

## Packaging & Ordering Information

Size	Weight	Part Number
1.2mm	15kg	200385

Disclaimer: The above information is provided as a guide; actual welding current and voltage will depend on the welding machine characteristics, which will vary from model to model. Other variables include run length and size, plate thickness, operator technique and gas type (if used). The user must evaluate the process, application and recommended professional advice. Under no circumstance will Dynaweld or its affiliates be liable for misuse or application of products this is entirely up to the user's ability.

[www.dynaweld.com.au](http://www.dynaweld.com.au)

Dynaweld Industrial Supplies Pty Ltd is the official Australian distributor for INE products | +61 2 8761 6500