

### Key Facts

- 5% Mn Tig wire
- Consistent quality
- Precision layer wound, double diamond shaved wire
- Excellent feedability and arc control
- Very high quality welds
- Suitable for a range of aluminium materials

### Description

Precision layer wound aluminium MIG wire providing smooth, consistent feeding. 5% Mg is considered to be the most commonly used aluminium wire due to its versatility and high strength.

### Recommended Shielding Gas

100% Ar

### Classification, Approvals & Conformances

AWS A5.10.ER5356

### Welding Positions

All positions

### Applications

Uses include storage tanks, boat building, bull bars, automotive and general aluminium fabrication. Suitable for welding a wide range of cast and wrought aluminium alloys.

- General aluminium fabrication and repairs
- Bull bars and rollbars
- Boat building
- Welding of many aluminium alloys

### Typical Analysis/Composition

Mn - Manganese	Cu - Copper	Mg - Magnesium	Others
< 0.05 – 0.20	< 0.10	4.5 – 5.5	< 0.15
Cr - Chromium	Ti - Titanium	Si - Silicon	Zn - Zinc
0.05 – 0.20	0.06 – 0.20	<0.25	< 0.10
Fe - Iron			
< 0.40			

### Typical Weld Mechanical Properties

<b>0.2% Proof Stress:</b>	> 110N/mm <sup>2</sup>
<b>Tensile Strength:</b>	350 – 370N/mm <sup>2</sup>
<b>Elongation:</b>	17%

### Packaging & Ordering Information

Size	Weight	Part Number
1.6mm	1kg	300008H
2.4mm	1kg	300009H
2.4mm	5kg	300009N
3.2mm	1kg	300010H
3.2mm	5kg	300010N

Disclaimer: The above information is provided as a guide; actual welding current and voltage will depend on the welding machine characteristics, which will vary from model to model. Other variables include run length and size, plate thickness, operator technique and gas type (if used). The user must evaluate the process, application and recommended professional advice. Under no circumstance will Dynaweld or its affiliates be liable for misuse or application of products this is entirely up to the user's ability.